



TDS

Model Number : H-300

| | | |
|-----------------------|--|--|
| Type | EVA Hot Melt Adhesive for Edge Banding | |
| Model Number | H-300 | |
| Composition | Ethylene-Vinyl Acetate (EVA), rosin ester, petroleum resin, antioxidant | |
| Appearance | No fillers, beige oval-shaped translucent solid granules | |
| Packaging | Net weight 25kg per bag, packaged in PP woven bag | |
| Technical Parameters | Brookfield Viscosity (cps) | 150°C: 45,000-50,000 180°C: 22,000-27,000 |
| | Density (g/cm ³) | approx.1.00 |
| | Softening Point (°C) | 85±2 |
| | Application Roller Temperature (°C) | 140-170 |
| Operating Temperature | Feed speed(m/min) | 4-15 |
| | Pressure (kg/cm ²) | 3-5 |
| | | |
| Characteristics | Good initial tack, good peel strength, enhanced flowability, improve adhesion on low-surface-energy substrates | |
| Cleaning | Remove uncured adhesive with a scraper, followed by adding paraffin wax to melt and clean | |
| Storage | Shelf life of at least 18 months if stored in a cool and dry place | |

Risk Warning:

If the operating temperature exceeds the specified maximum limit for an extended period, the hot melt adhesive may decompose and produce harmful substances. Good ventilation can eliminate the odor released by the hot melt adhesive. For high-temperature operations, take proper protective measures.

Scope of Use:

Suitable for manual edge banding machines. Application: PVC, ABS, veneer, thin wood flakes, decorative paper etc, broad compatibility.

Application Guidelines:

1. Compatible equipment: Manual edge banding machines.
2. Compatible substrates: Particleboard, plywood, Medium-Density Fiberboard (MDF), eco-friendly board etc, especially for non-heat-resistant thin PVC edge banding tape (0.4mm thickness).
3. Apply sufficient pressure and adequate adhesive thickness during manual edge banding operations to make sure strong bonding.



惠州优胜盈创新材料有限公司

广东省州市博罗县石湾镇浚源路南侧地段
电话: 0752-6618779 传真: 0752-6618779
网址: <http://www.u-winchina.com/>